









Product properties	
<b>Format</b>	2200 x 185 x 13 mm
Top layer	≥ 3.6 mm
<b>Packaging</b>	9 Elements
Pack	3.663 m <sup>2</sup> / 29.304 Kg
Pallet	32 Packs 117.216 m <sup>2</sup> / 937.728 Kg
<b>Warranty</b>	25 years
Notes	- cleaning an maintenance see intruction - technical changes reserved

Product labeling	
 EN 14342 : 08	      

Tolerances (EN 13489)	
Admissible difference in length (± 0.1 %)	± 0.05 %
Admissible difference in width (± 0.2 mm)	± 0.1 mm
Squareness of the element (≤ 0.1 %)	≤ 0.05 %
Longitudinal curvature along the element (≤ 0.1 %)	≤ 0.05 %
Transverse curvature across the width (≤ 0.1 %)	≤ 0.08 %
Height differences of elements (≤ 0.2 mm)	≤ 0.18 mm
Moisture content at the time of first delivery (5-9%)	6 – 8 %

Classification Specifications			
		Testing standard	Valuation
	Resistance to roller castor chairs	EN 425	We recommend the use of a conventional chairmat
	Effect of a furniture leg	EN 424	No visible changes
	<b>Thermal conductivity</b> Underfloor heating – suitable, with the backing material an vapor barrier	EN 12664	0.087 m <sup>2</sup> *K/W
	Formaldehyde (E1 = 0.1 ppm)	EN 717-1	≤ 0.05 ppm
	Acoustical impact noise reduction	ISO 717-2	12 db (with Akustic-Protect 100)
	Disposal		Privat waste disposal with normal haushold waste, bulky waste possible

Classification surface properties				
		Testing standard	Valuation	
			Lacquer	Naturoil
	Slip resistance	EN 13893	μ ≥ 0.47	μ ≥ 0.47
		CEN/TS 15676	29 SRT (SRV wet)	46 SRT (SRV wet)
			51 SRT (SRV dry)	103 SRT (SRV dry)
	Reaction to fire, click-installation as a floating floor	EN 13501-1	D <sub>fl</sub> s1	
	Reaction to fire, installation by all-over adhesion	EN 13501-1	D <sub>fl</sub> s1	
	Chemical resistance	EN 13442	Category 5	Category 4
	Bond strength / Gross cut test	ISO 2409	0	n.n.
	Slip reststance, inclined plane	DIN 51130	R 9	R 10

Changed:	QMB	File name:	PA_TDS_Parkett_Classic_EN_2014
Date:	01.08.2013	Update:	<a href="http://www.parador.de">www.parador.de</a>
Our TDS will be constantly updated and adapted to the prior art. This version replaces all previous versions and is valid from:			
			01.03.2014

Free sorting according to EN 13489								
Assortment:	Block							
Characteristics according to EN 1310:	Upper side of the lamella							
Type of wood:	Canadian maple		Mountain maple, european			Beech		
Botanical designation / Code (EN 13556):	Acer saccharum Marsh. / ACSC		Acer pseudoplatanus L. / ACPS			Fagus sylvatica L. / FASY		
Origin:	CA		BA, HR			HU, HR, SK, BA		
Shortcut / sorting / date (internal):	ES-L-AHC		ER-L-BAH			ER-L-BU		
	Version 3 2012		Version 4 2012			Version 4 2012		
	N2	N3	N1	N2	N3	N1	N2	N3
Sorting:	Natur	Living	Select	Natur	Living	Select	Natur	Living
Sound sapwood	-	-	-	-	-	-	-	-
Knot (intergrown)	not permitted	permitted: up to 10 mm	not permitted	not permitted	permitted: up to 30 mm	not permitted	not permitted	permitted: up to 20 mm
Falling out knot	not permitted	not permitted	not permitted	not permitted	not permitted	not permitted	not permitted	not permitted
Pinkknots	permitted: up to 2 mm	permitted	not permitted	permitted: up to 2 mm	permitted: up to 8 mm	not permitted	permitted: up to 2 mm	permitted
Filling	not permitted	permitted	not permitted	not permitted	permitted: up to 5 mm	not permitted	not permitted	permitted: up to 5 mm
Slight crack/ haircrack	not permitted	not permitted	not permitted	not permitted	not permitted	not permitted	not permitted	not permitted
Sugar inclusions, mineral inclusions	permitted: black stripes	permitted	permitted: a few	permitted: Colourinclusions up to 50 mm	permitted	permitted: a few	permitted: Colour inclusions up to 30 mm	permitted
Bark pocket	not permitted	not permitted	not permitted	not permitted	not permitted	not permitted	not permitted	not permitted
Lightning cracks	not permitted	permitted	not permitted	not permitted	not permitted	not permitted	not permitted	permitted
Slope of grain	not permitted: extreme flader	permitted	not permitted: extreme flader	all features permitted	permitted	not permitted: extreme flader	permitted: extreme flader	all features permitted
Healthy heart	not permitted	permitted	not permitted	not permitted	permitted	not permitted	not permitted	permitted
Medullary ray	not permitted	not permitted	permitted	permitted	permitted	permitted	permitted	permitted
Discoloration, colour variation	permitted: slight color variation	permitted: all colours	permitted: slight color variation	permitted: all colours	permitted: all Colours	permitted: slight color variation	permitted: all colours	permitted: all Colours, blueness
White streaks	-	-	-	-	-	-	-	-
Pilling sticks marking	not permitted	not permitted	not permitted	not permitted	not permitted	not permitted	not permitted	not permitted
Biodeterioration (EN 1311)	not permitted	not permitted	not permitted	not permitted	not permitted	not permitted	not permitted	not permitted
<b>Non-visible parts</b>								
All features without restrictions to size or quantity permitted, provided they do not affect the strength or durability of the floor.								
<b>Comment</b>								
Maximum 3% of lamellas are allowed in the next lower grading. Wood is a natural product and therefore different in color and texture. Samples, brochures and photos are therefore only approximate and not binding. The action of sunlight affects the natural variation in wood shade. This allows the product present at the time of delivery of significant differences to master.								

Changed:	QMB	File name:	PA_TDS_Parkett_Classic_Anhang_EN_2014
Date:	01.05.2013	Update:	<a href="http://www.parador.de">www.parador.de</a>
Our TDS will be constantly updated and adapted to the prior art. This version replaces all previous versions and is valid from:			01.03.2014
			Page 1 of 4

Free sorting according to EN 13489										
Assortment:	Block									
Characteristics according to EN 1310:	Upper side of the lamella									
Type of wood:	Oak	Ash	European cherry steamed		American walnut					
Botanical designation / Code (EN 13556):	Quercus petraea Liebl., Quercus robur L. / QCXE	Fraxinus excelsior L. / FXEX	Prunus avium L. / PRAV		Juglans nigra L. / JGNG					
Origin:	DE, AT, HU, HR, SK, BA, UA, RS, FR, CZ		HU, HR		BA, HR		US			
Shortcut / sorting / date (internal):	ER-L-EI				ER-L-ES	ES-L-KIR eur		ER-L-SWN		
	Version 8 2014				Version 6 2012	Version 3 2012		Version 3 2012		
	N1	N2	N3	N4	N3	N2	N3	N2	N3	
Sorting:	Select	Natur	Living	Living astig	Living	Natur	Living	Natur	Living	
Sound sapwood	not permitted	not permitted	permitted	permitted	-	permitted: up to 10 mm	not permitted	permitted	permitted	
Knot (intergrown)	not permitted	not permitted	not permitted	permitted: up to 30 mm	permitted: up to 30 mm	not permitted	permitted: up to 15 mm	permitted: up to 30 mm	permitted: up to 30 mm	
Falling out knot	not permitted	not permitted	not permitted	permitted: up to 10 mm	not permitted	not permitted	not permitted	not permitted	permitted: up to 8 mm	
Pinkknots	not permitted	permitted: up to 2 mm	permitted: up to 10 mm	permitted: clusters of knots	permitted: up to 3 mm	permitted: up to 3 mm	permitted	permitted: up to 3 mm	permitted	
Filling	not permitted	not permitted	permitted: up to 5 mm	permitted: up to 10 mm	permitted: up to 3 mm	not permitted	permitted: up to 8 mm	permitted: up to 3 mm	permitted: up to 8 mm	
Slight crack/ haircrack	not permitted	not permitted	not permitted	not permitted	not permitted	not permitted	not permitted	not permitted	permitted	
Sugar inclusions, mineral inclusions	-	-	-	-	permitted	-	-	-	-	
Bark pocket	not permitted	not permitted	not permitted	not permitted	permitted	not permitted	not permitted	not permitted	not permitted	
Lightning cracks	not permitted	not permitted	permitted	permitted	not permitted	-	-	not permitted	permitted	
Slope of grain	not permitted: extreme flader	not permitted: extreme flader	all features permitted	all features permitted	all features permitted	not permitted: extreme flader	all features permitted	all features permitted	all features permitted	
Healthy heart	-	-	-	permitted	permitted	-	-	-	-	
Medullary ray	permitted	permitted	permitted	permitted	permitted	-	-	-	-	
Discoloration, colour variation	permitted: slight color variation	permitted: all colours, a few dark stripes	permitted: all colours	permitted: all colours, slight color variation	permitted: all colours	permitted: slight color variation	permitted: all colours	permitted: all colours	permitted: all colours	
White streaks	not permitted	permitted	permitted	permitted	not permitted	not permitted	not permitted	-	-	
Pilling sticks marking	not permitted	not permitted	not permitted	not permitted	not permitted	not permitted	not permitted	not permitted	not permitted	
Biodeterioration (EN 1311)	not permitted	not permitted	not permitted	not permitted	not permitted	not permitted	not permitted	not permitted	not permitted	
Non-visible parts										
All features without restrictions to size or quantity permitted, provided they do not affect the strength or durability of the floor.										
Comment										
Maximum 3% of lamellas are allowed in the next lower grading. Wood is a natural product and therefore different in color and texture. Samples, brochures and photos are therefore only approximate and not binding. The action of sunlight affects the natural variation in wood shade. This allows the product present at the time of delivery of significant differences to master.										

Changed:	QMB	File name:	PA_TDS_Parkett_Classic_Anhang_EN_2014
Date:	01.05.2013	Update:	<a href="http://www.parador.de">www.parador.de</a>
Our TDS will be constantly updated and adapted to the prior art. This version replaces all previous versions and is valid from:		01.03.2014	Page 2 of 4

Free sorting according to EN 13489										
Assortment:	Wide plank									
Characteristics according to EN 1310:	Upper side of the floor board									
Type of wood:	<b>Oak</b>							<b>Ash</b>	<b>Larch</b>	
Botanical designation / Code (EN 13556):	Quercus petraea Liebl., Quercus robur L. / QCXE							Fraxinus excelsior L. / FXEX	Larix decidua Mill. / LADC	
Origin:	DE, AT, HU, HR, SK, BA, UA, RS, FR, CZ							HU, HR	AT	
Shortcut / sorting / date (internal):	ER-LH-EI				ER-LH-EI ger.		ER-LH-EI themo	ER-LH-ES	ER-LH-LÄR	
	Version 5 2013				Version 2 2011		Version 1 2012	Version 1 2011	Version 2 2011	
	LH N2	LH N3	LH N4	LH N4	LH N3	LH N6	LH N4	LH N4	LH N5	
Sorting:	Select	Natur	Living	Living	Rustikal	Living	Natur	Living	Rustikal	
Sound sapwood	not permitted	not permitted	permitted: up to 30 mm	permitted	not permitted	permitted: up to 30 mm	not permitted	-	not permitted	
Knot (intergrown)	permitted: up to 20 mm	permitted: up to 30 mm	permitted: up to 50 mm	permitted: up to 80 mm	permitted: up to 4 mm	permitted: up to 50 mm	permitted: up to 50 mm	permitted: up to 30 mm	permitted: up to 25 mm	
Falling out knot	not permitted	permitted: up to 15 mm	permitted: up to 35 mm	permitted: up to 30 mm	not permitted	permitted: up to 20 mm	permitted: up to 30 mm	permitted: up to 15 mm	permitted: up to 25 mm	
Pinkknots	permitted: cluster of knots	permitted: cluster of knots	permitted: cluster of knots	permitted: cluster of knots	permitted: up to 3 mm	permitted: cluster of knots	permitted: cluster of knots	permitted	permitted	
Filling	permitted	permitted	permitted	permitted	permitted	permitted	permitted	permitted: up to 10 mm	permitted	
Slight crack/ haircrack	not permitted	not permitted	permitted	permitted	not permitted	permitted	not permitted	not permitted	permitted	
Sugar inclusions, mineral inclusions	-	-	-	-	-	-	-	-	permitted	
Bark pocket	not permitted	not permitted	not permitted	not permitted	not permitted	not permitted	not permitted	not permitted	permitted	
Lightning cracks	permitted: in knots	permitted: in knots	permitted: in knots	permitted	not permitted	permitted	permitted	permitted	permitted	
Slope of grain	permitted	permitted	permitted	permitted	permitted	permitted	permitted	permitted	permitted	
Healthy heart	not permitted: coretube	not permitted: coretube	not permitted: coretube	not permitted	not permitted	not permitted	not permitted	permitted	-	
Medullary ray	permitted	permitted	permitted	permitted	permitted	permitted	permitted	permitted	-	
Discoloration, colour variation	permitted: slight color variation	permitted: slight color variation	permitted: slight color variation	permitted	permitted: slight color variation	permitted: slight color variation	permitted: slight color variation	permitted	permitted: slight color variation	
White streaks	not permitted	not permitted	not permitted	not permitted	not permitted	not permitted	permitted	-	-	
Pilling sticks marking	not permitted	not permitted	not permitted	not permitted	not permitted	not permitted	not permitted	not permitted	not permitted	
Biodeterioration (EN 1311)	not permitted	not permitted	not permitted	not permitted	not permitted	not permitted	not permitted	not permitted	not permitted	
* Sorted after the surface finish										
Non-visible parts										
All features without restrictions to size or quantity permitted, provided they do not affect the strength or durability of the floor.										
Comment										
Maximum 3% of floor board are allowed in the next lower grading. Wood is a natural product and therefore different in color and texture. Samples, brochures and photos are therefore only approximate and not binding. The action of sunlight affects the natural variation in wood shade. This allows the product present at the time of delivery of significant differences to master.										

Changed:	QMB	File name:	PA_TDS_Parkett_Classic_Anhang_EN_2014
Date:	01.05.2013	Update:	<a href="http://www.parador.de">www.parador.de</a>
Our TDS will be constantly updated and adapted to the prior art. This version replaces all previous versions and is valid from:			01.03.2014
			Page 3 of 4

Free sorting according to EN 13489				
Assortment:	Fineline pattern			
Characteristics according to EN 1310:	Upper side of the lamella			
Type of wood:	Mountain maple, european	Oak	Ash	American walnut
Botanical designation / Code (EN 13556):	Acer pseudoplatanus L. / ACPS	Quercus petraea Liebl., Quercus robur L. / QCXE	Fraxinus excelsior L. / FXEX	Juglans nigra L. / JGNG
Origin:	BA, HR	DE, AT, HU, HR, SK, BA, UA, RS, FR, CZ	HU, HR	US
Shortcut / sorting / date (internal):	ER-BAH	ER-L-EI	ER-L-ES	ER-LH-SWN
	Version 1 2011	Version 1 2011	Version 1 2011	Version 1 2011
Sorting:	Natur	Natur	Natur	Natur
Sound sapwood	-	permitted	-	permitted
Knot (intergrown)	permitted: up to 30 mm	permitted	permitted: up to 30 mm	permitted
Falling out knot	not permitted	not permitted	not permitted	not permitted
Pinkknots	permitted: up to 8 mm	permitted	permitted: up to 3 mm	permitted
Filling	permitted: up to 5 mm	permitted	permitted: up to 3 mm	permitted
Slight crack/ haircrack	not permitted	-	not permitted	permitted
Sugar inclusions, mineral inclusions	-	-	permitted	-
Bark pocket	not permitted	not permitted	not permitted	not permitted
Lightning cracks	not permitted	-	not permitted	-
Slope of grain	permitted	-	permitted	permitted
Healthy heart	permitted	permitted	permitted	-
Medullary ray	permitted	permitted	permitted	-
Discoloration, colour variation	permitted	permitted	permitted	permitted
White streaks	permitted	permitted	permitted	permitted
Pilling sticks marking	not permitted	not permitted	not permitted	not permitted
Biodeterioration (EN 1311)	not permitted	not permitted	not permitted	not permitted
Non-visible parts				
All features without restrictions to size or quantity permitted, provided they do not affect the strength or durability of the floor.				
Comment				
Maximum 3% of lamellas are allowed in the next lower grading. Wood is a natural product and therefore different in color and texture. Samples, brochures and photos are therefore only approximate and not binding. The action of sunlight affects the natural variation in wood shade. This allows the product present at the time of delivery of significant differences to master.				

Changed:	QMB	File name:	PA_TDS_Parkett_Classic_Anhang_EN_2014	
Date:	01.05.2013	Update:	<a href="http://www.parador.de">www.parador.de</a>	
Our TDS will be constantly updated and adapted to the prior art. This version replaces all previous versions and is valid from:			01.03.2014	Page 4 of 4