
AirMaster[®] Oxy

Preliminary specification according to EN 1307

Type of manufacture	ISO 2424		Tufted ?	1/10 "					
Aspect	ISO 2424		Structured loop pile						
Dye method			Solutior	n dyed					
Dimensions	EN 994	50 x 50 / 19,68" x 19,68" (20 tiles per box)							
Primary backing	ISO 2424		Polyester fleece						
Secondary backing	ISO 2424	Desso ProBase Polyver® - Polyscan®							
Pile fibre composition	ISO 2424	BCF Polyamide 6 and ECONYL [®] (ECONYL [®] is made from 100% regenerated content) **							
Total thickness	ISO 1765	mm	6.0		inch	0.2			
Effective pile thickness	ISO 1766	mm	3.0		inch	0.12			
Total mass	ISO 8543	g/m²	4250		oz/yd²	125.4			
Total pile mass	ISO 2424	g/m²	670		oz/yd²	19.8			
Effective pile mass	ISO 8543	g/m²	460		oz/yd²	13.6			
Pile density	ISO 8543	g/cm³	0.153		lb/in ³	0.0055			
Number of tufts	ISO 1763	/dm²	1580		/yd²	132104			
Stroll test	ISO 6356	kV	≤ 2,0						
Vertical resistance	ISO 10965	Ohm	≤ 1 x 10) ⁹					
Horizontal resistance	ISO 10965	Ohm	≤ 1 x 10 ⁹						
Use classification	EN 1307	33 Commercial - heavy use							
Luxury rating	EN 1307		LC 2						
Dimensional stability	EN 986	%	≤ 0,2						
Impact sound reduction ΔL_w	ISO 10140	dB	24						
Sound absorption	ISO 354	Freq. Hz	125	250	500	1000	2000	4000	
		α _s	0.00	0.02	0.06	0.17	0.27	0.34	
Noise reduction	ISO 354	α _w	0.15						
Thermal resistance	ISO 8302	m².K/W	-						
Flammability	EN 13501-1		Bfl - s1 (loose laid tested)						
Prodis - GUT	www.pro-dis.	www.pro-dis.info		DC3FBDAC					



** ECONYL® is a yarn made from 100% regenerated content. The total % of regenerated content varies per product and per colour. Whether a colour contains ECONYL® and the exact % thereof can be found on our website: www.desso.com.

Desso flooring products are to be installed in full accordance with Desso's installation instructions and recognised trade standards. An effective, regular cleaning and maintenance programme is vital for retaining a high appearance level. Desso flooring products should only be used as floorcoverings. Note: Desso reserves the right to amend this specification without giving prior notice. For the latest versions of the technical specifications, visit www. desso.com

EN-20150518

